

**Technical data sheet**
**Membrana Vaxo<sup>®</sup> S**

Characteristic	Test method	Unit	Result	Tolerance	
				Min.	Max.
Lenght	EN 1848 -2	m	50	0	+0,5
Width	EN 1848 -2	m	1,5	-0,005	+0,005
Straightness	EN 1848 -2	-	Pass	-	-
Mass per unit area	EN 1848 -2	g/m <sup>2</sup>	100	-15	+15
Thickness	EN 1848 -2	mm	0,4	-0,2	+0,2
Reaction to fire (free-hanging)	EN 11925-2	class	F	-	-
Resistance to water penetration	EN 1928 A	class	W1	-	-
Water vapour transmission Properties	EN ISO 12572 C	m	0,03	-0,015	+0,015
Resistance to penetration of air	EN 12114	m <sup>3</sup> /(m <sup>2</sup> x h x 50 Pa)	Max 0,05	-	-
Tensile properties: Maximum tensile force	EN 12311-1	N/50mm	MD 185	-55	+55
			CD 110	-35	+35
Tensile properties: elongation	EN 12311-1	%	MD 70	-50	+50
			CD 110	-60	+60
Resistance to tearing (nail shank)	EN 12310-1	N	MD 90	-50	+50
			CD 125	-50	+50
Dimensional Stability	EN 1107-2	%	2	-	-
Stability at low temperature	EN 1109	°C	-40	-	-
Artificial ageing by long term exposure to the combination Of UV radiation and elevated Temperatura and heat (80°C)	Elongation EN 13859-1 annex C	%	MD 40	-25	+25
			CD 45	-25	+25
	Tensile strength EN 13859-1 annex C	N/50mm	MD 160	-35	+35
			CD 85	-25	+25
Resistance to water penetration EN 13859-1 annex C	class	W1	-	-	
Water vapour transmission 23°C/85%RH	Lyssy	g/m <sup>2</sup> x 24h	1500	-250	+250
Water vapour transmission 38°C/90%RH	Lyssy	g/m <sup>2</sup> x 24h	3500	-400	+400

The above product technical data sheet will be valid form 01.01.2019

 Bielsko Biała,  
 Place and date of issue

8.06.2018